



PIA-TEST METHOD-6010

03 May 2007

**Superseding
FED. TEST METHOD STD.
NO. 191A METHOD 6010
20 July 1978**

The following commercial specification is adopted from the military document. Revision A included all known accepted revisions, amendments, notices, and Department of Defense (DoD) engineering changes previously developed for this item. Revisions B and forward include changes adopted to reflect technology and design evolution

SHRINKAGE OF CORDAGE, BOILING WATER METHOD; DETERMINATION OF

The Parachute Industry Association makes this document available for use by Industry and Government organizations that wish to apply this specification to their products.

1. SCOPE

1.1 Scope. This method is intended for determining the residual shrinkage of cordage.

2. TEST SPECIMEN

2.1 Test Specimen. The specimen shall be a single length of 24 inches (610 mm) cut from the sample unit.

3. NUMBER OF DETERMINATIONS

3.1 Number of determinations. Unless otherwise specified in the procurement document three determinations shall be made from each sample unit.

4. APPARATUS

4.1 Container. A container of suitable size so that the required specimens can be completely immersed in water when being tested.

4.2 Weights. Weights of suitable size that will cause the specimen to be completely submerged.

4.3 Measurement stick or metal tape. Yardstick, meterstick, metal tape or other suitable measuring device graduated in increments of 1/16 inch (1 mm).

DISTRIBUTION STATEMENT: All Rights Reserved. No Part of this publication may be reproduced without prior written permission from Parachute Industry Association. Additional copies may be purchased on-line from the PIA Store at: www.pia.com.